

- 14 -

Abstract of the Disclosure

A cylindrical protruding portion 24 and a cylindrical stepped portion 25 are arranged in a metal collar 20. Shrinkage of resin 30 after injection-molding may form a gap in an interface 50 between the protruding portion 24 and the resin 30. However, in an interface 51 between the stepped portion 25 and the resin 30, the resin 30 presses the cylindrical stepped portion 25 and does not form a gap. Thereby, formation of a continuous gap is prevented, and entry of moisture is prevented.